
TP×× SF Series

Silicone Free Gap Filler Pad

TP××-SF series silicone-free thermal pads designed for are silicone sensitivity Sensing application and design, development of a high thermal conductivity, high Strength, flame retardant interface thermal conductive materials. for different The application of the development of a number of models meet High compression. can multiple heavy work. tear resistance, high frequency vibration Impact and other applications.

Featoure 30 du Renefitens.

- Naturally tacky, easing application
- Excellent, high volume applications
- Excellent electrical isolation



Typical Applications

- Fiber Optics
- Medical Device
- Hard Disc Driver
- Automotive Sensors and Modules
- Silicon Sensitive Components

Typical Properties			
Attribute	Value	Value	Test Method
	TP 200SF	TP 300SF	-
Composition	Acrylate	Acrylate	-
Color	Green	Blue	Visual
Thickness (mm)	1.0 to 3.0	1.0 to 10.0	ASTM D374
Density (g/cc)	2.8	3.0	ASTM D792
Hardness (Shore OO)	45	50	ASTM D2240
Usage Temperature (°C)	- 40 to 120	-40 to 125	-
Electrical			
Breakdown Voltage (kV/mm)	>6.0	≥ 6.0	ASTM D149
Flammability	V-1	V-1	UL 94
Thermal			
Thermal conductivity (W/m.K)	2.0	3.0	ISO 22007-2

Storage

Store in a cool, dry, well-ventilated place.

Shelf life

Shelf life of the product is 12 months after date of shipment

Any information provided in this document is considered accurate. All specifications are subject to change without notice. All products and services are sold under the terms and conditions of sale. Neither the seller nor the manufacturer is liable for any direct, incidental or consequential loss or damage to the infringement or contract, including loss of profits or income resulting from the use or inability to use the product. Unless the seller and the manufacturer's official sign the agreement, the seller or the purchaser's statement, purchase order or advice not included here shall have no effect or effect. © Copyright 2019, AOCHUAN TECHNOLOGY.






TP×× SF Series


Silicone Free Gap Filler Pad

Thickness vs. Thermal Resistance

Referen



Pressure vs. Deflection Reference



Any information provided in this document is considered accurate. All specifications are subject to change without notice. All products and services are sold under the terms and conditions of sale. Neither the seller nor the manufacturer is liable for any direct, incidental or consequential loss or damage to the infringement or contract, including loss of profits or income resulting from the use or inability to use the product. Unless the seller and the manufacturer's official sign the agreement, the seller or the purchaser's statement, purchase order or advice not included here shall have no effect or effect. $\mathbb O$ Copyright 2019, AOCHUAN TECHNOLOGY.



